



A REVOLUTIONARY PLATFORM  
CONNECTING VERIFIED **RECYCLERS** AND **PRODUCERS**  
FOR TRUSTED MATERIAL TRADE

CONNECT WITH US

+91 91361 48358

SUPPORT@CIRQEX.COM

Product Code - CIR0008CB

## rHDPE Black

rHDPE can be used for Pipe Extrusion.

### General Information

#### Condition

Granules

#### License

FSSAI

### Processing Methods

Blow molding

#### Source

Post Consumer



### Technical Properties

Property	Value	Unit
Melt Flow Rate 5kg, 190 C	0.2 ± 0.1	g/10min
Density @23°C	0.945±0.01	%
Moisture	<0.250	%
Ash Content	0.4 ± 0.1	%
Elongation at Break	40+10	%
Environmental Stress Crack Resistance	-	-
Izod impact strength	375+25	J/m
Flexural Modulus	1800+100	Mpa
Residual moisture content	-	-
Viscosity	-	-

### Compliance Status

EPR Registration	✓
Annual Report (FY 24-25)	✗
GST E-invoice	✓
CTO Validity	✗
Financial Compliance	✗
ISO Certification	✓
Other Available Certifications	On Request

**Product Feature:** This grade developed entirely from 100% post-consumer recycled plastic waste and provides multiple brands and producers a sustainable solution to meet their environmental commitments seamlessly.

**Disclaimer:** The information provided in this datasheet represents typical characteristics of the recycled material and is intended for general guidance only. Variations in raw material input, recycling methods, and processing conditions may result in differences in the properties and performance of the final product. It is the responsibility of the customer to verify the suitability of the material for their specific application through appropriate testing and evaluation. CIRQ Ventures (OPC) Private Limited makes no warranties, express or implied, including but not limited to warranties of merchantability or fitness for a particular purpose. Under no circumstances shall CIRQ Ventures (OPC) Private Limited be liable for any direct, indirect, incidental, or consequential damages arising from the use or reliance on the information provided. Customers should ensure compliance with all relevant regulatory and quality standards prior to use.