



A REVOLUTIONARY PLATFORM  
CONNECTING VERIFIED **RECYCLERS** AND **PRODUCERS**  
FOR TRUSTED MATERIAL TRADE

CONNECT WITH US

+91 91361 48358    SUPPORT@CIRQEX.COM

Product Code - CIR0008FW1

## rPP White

rPP can be used for Rafia Tapes for woven sacks, FIBC and for furniture.



### General Information

**Condition**

Granules

**License**

Non FSSAI

**Processing Methods**

Extrusion

**Source**

Post Consumer

Technical Properties		
Property	Value	Unit
Melt Flow Rate @ 2.16kg, 230 C	7 ± 2	g/10min
Density @23°C	120±0.05	gm/cm
Moisture	<0.25	%
Tensile Strength at Maximum Load	18 ± 2	MPa
Ash Content	40 ± 5	%
Environmental Stress Crack Resistance	-	-
Izod impact strength	40 ± 5	J/m
Flexural Modulus	1000±100	Mpa
Residual moisture content	-	-
Viscosity	-	-

Compliance Status	
EPR Registration	✓
Annual Report (FY 24-25)	✗
GST E-invoice	✓
CTO Validity	✗
Financial Compliance	✗
ISO Certification	✓
Other Available Certifications	On Request

**Product Feature:** This grade developed entirely from 100% post-consumer recycled plastic waste and provides multiple brands and producers a sustainable solution to meet their environmental commitments seamlessly.

**Disclaimer:** The information provided in this datasheet represents typical characteristics of the recycled material and is intended for general guidance only. Variations in raw material input, recycling methods, and processing conditions may result in differences in the properties and performance of the final product. It is the responsibility of the customer to verify the suitability of the material for their specific application through appropriate testing and evaluation. CIRQ Ventures (OPC) Private Limited makes no warranties, express or implied, including but not limited to warranties of merchantability or fitness for a particular purpose. Under no circumstances shall CIRQ Ventures (OPC) Private Limited be liable for any direct, indirect, incidental, or consequential damages arising from the use or reliance on the information provided. Customers should ensure compliance with all relevant regulatory and quality standards prior to use.