



Product Code - CIR008AW

rLDPE White

rLDPE can be used for milk, curd, butter milk, cream, water packaging etc.

General Information

Condition

Granules

License

Non FSSAI

Processing Methods

Blown Film

Source

Post Consumer



Technical Properties		
Property	Value	Unit
Melt Flow Rate, 2.16 kg, 190 C	0.65 ± 0.10	g/10min
Density	0.945 ± 0.01	gm/cm3
Moisture	<0.5	%
Tensile Strength	1915 ± 2	MPa
Ash Content	3±2	%
Elongation at Break	350 ± 50	%
Environmental Stress Crack Resistance	-	-
Izod impact strength	NB	J/m
Flexural Modulus	300 ± 50	Mpa
Residual moisture content	On	-
Viscosity	-	-

Compliance Status	
EPR Registration	✓
Annual Report (FY 24-25)	X
GST E-invoice	✓
CTO Validity	X
Financial Compliance	X
ISO Certification	✓
Other Available Certifications	On Request

PRODUCT FEATURES: This grade developed entirely from 100% post-consumer recycled plastic waste and provides multiple brands and producers a sustainable solution to meet their environmental commitments seamlessly.

Disclaimer: The information provided in this datasheet represents typical characteristics of the recycled material and is intended for general guidance only. Variations in raw material input, recycling methods, and processing conditions may result in differences in the properties and performance of the final product. It is the responsibility of the customer to verify the suitability of the material for their specific application through appropriate testing and evaluation. CIRQ Ventures (OPC) Private Limited makes no warranties, express or implied, including but not limited to warranties of merchantability or fitness for a particular purpose. Under no circumstances shall CIRQ Ventures (OPC) Private Limited be liable for any direct, indirect, incidental, or consequential damages arising from the use or reliance on the information provided. Customers should ensure compliance with all relevant regulatory and quality standards prior to use.